

J-Fix Hammer In Capsules Epoxy Acrylate



For Use With Flat Ended Studs

J-Fix Hammer In Capsules Epoxy Acrylate											
Part Number	Capsule Diameter mm	Capsule Length mm	Rebar				Threaded Rods				
			Nominal Diameter	Drill Diameter	Hole Depth		Nominal Diameter	Drill Diameter	Hole Depth		
					Single	Double			Single	Double	
JCAPHM10	11	80	10	13	100	200	10	12	100	200	
JCAPHM12	13	95	12	15	120	240	12	14	120	240	
JCAPHM16	17	95	16	20	160	320	16	18	125	250	
JCAPHM20	22	175	20	25	200	400	20	25	200	400	
JCAPHM24	24	210	25	30	250	500	24	28	240	480	
JCAPHM30	33	265	32	30	250	500	30	35	300	600	

Cure Times		
Base Material Temp °C	Cure Time Dry Concrete minutes	Cure Time Wet Concrete minutes
5	300	600
10	120	240
20	60	120
30	45	90

Capsule Temperature Must Be Between +5 To +25 Degree C

Epoxy Acrylate Hammer In Capsules Suitable For Use In Solid Concrete And Some Natural Stone
 Expansion Free - High Loads - Increased Embedment Depth - Rapid Installation
 Can Achieve High Loads By Using 2 Capsules At Double Embedment Depth



Drill Correct Diameter Hole To Correct Depth



Clean Out By Brushing And Blowing Out To Remove Dust And Debris



Insert Capsule Or Capsules



Hammer In Rebar Or Threaded Rod Take Care Not To Damage The End Of The Threaded Rod



Allow To Cure For Appropriate Time